

DOBAU – PipeProtect Din

Tekinskt Datablad



Sida

1-2 Svenska

3 Engelska

Besöksadress

EP Membran AB

Arntorpsgatan 5 • 442 45 Kungälv • Sverige

Telefon: 0303 77 03 03

Epost: Info@epmembran.se

Hemsida: www.Epmembran.se

DOBAU – PipeProtect Din



Petrolatum – korrosionsskyddsbeläggning enligt DIN EN 12068

Användning

DOBAU- Pipeprotect din är en Korrosionsskyddstejpen för efterbeläggning av svetsfogar, formstycken, armaturer, husanslutningar, flänsar samt inom blixtskyddskonstruktioner. Särskilt lämplig för svåråtkomliga områden.

Appliceringsanvisningar

Ytan som ska beläggas måste avrostas noggrant med stålborste och rengöras. Ytan ska vara torr och fri från fett. Beläggningen appliceras spiralförmått med minst 50 % överlapp och ska börja och sluta 50 mm in på den intilliggande fabriksbeläggningen. Den laminerade filmen ska ligga utåt. Se till att lindningen sker utan veck och utan hålrum. Särskilt i överlappningsområdet ska bandaget pressas fast och slätas ut igen.

Teknisk Data

DOBAU- PipeProtect din består av en kemfiberarmering (185 g/m²), belagd på båda sidor med en modifierad petrolatummassa med hög vidhäftning och elasticitet, applicerad på en HDPE-bärfilm.

Tjocklek:	1.5 mm ± 0.1 mm
Vikt:	ca 1,9 kg/m ²
Färg:	beige till brun

Belastningsklass

Klass A, drifttemperatur upp till 30 °C.

Besöksadress

EP Membran AB

Arntorpsgatan 5 • 442 45 Kungälv • Sverige

Telefon: 0303 77 03 03

Epost: Info@epmembran.se

Hemsida: www.Epmembran.se

DOBAU - PipeProtect Din



Petrolatum – korrosionsskyddsbeläggning enligt DIN EN 12068

Lagring

Skyddas från direkt solljus. Förvaras torrt och stående på kapkanten. Högsta staplingshöjd: 4 kartonger.

Leveransform

Rullängd: 10 m

Bredd (mm): 50, 100, 150, 200

Förpackningsenhet/kartong: 24 (50 mm), 8 (100 mm), 12 (150 mm), 3 (200 mm)

Besöksadress

EP Membran AB

Arntorpsgatan 5 • 442 45 Kungälv • Sverige

Telefon: 0303 77 03 03

Epost: Info@epmembran.se

Hemsida: www.Epmembran.se

DOBAU – PipeProtect Din



Petrolatum Corrosion Protection Coating according to DIN EN 12068

Application

DOBAU – PipeProtect DIN is a corrosion protection tape for post-coating of welded joints, fittings, valves, house connections, flanges and lightning protection constructions. Particularly suitable for hard-to-reach areas.

Application Instructions

The surface to be coated must be thoroughly derusted using a steel brush and cleaned.

The surface must be dry and free from grease.

The coating is applied spirally with at least 50% overlap and must begin and end 50 mm onto the adjacent factory coating.

The laminated film must face outward.

Ensure wrinkle-free wrapping without voids.

Particular attention must be paid in overlap areas where the tape should be firmly pressed and smoothed again.

Technical Data

DOBAU – PipeProtect DIN consists of a chemical fiber reinforcement (185 g/m²), coated on both sides with a modified petrolatum compound with high adhesion and elasticity, applied to an HDPE carrier film.

Thickness: 1.5 mm ± 0.1 mm

Weight: approx. 1.9 kg/m²

Color: beige to brown

Load class: Class A

Operating temperature: up to 30 °C

Storage

Protect from direct sunlight.

Store dry and upright on the roll edge.

Maximum stacking height: 4 cartons.

Packaging

Roll length: 10 m

Widths (mm): 50, 100, 150, 200

Packaging unit/carton: 24 (50 mm), 8 (100 mm), 12 (150 mm), 3 (200 mm)

Besöksadress

EP Membran AB

Arntorpsgatan 5 • 442 45 Kungälv • Sverige

Telefon: 0303 77 03 03

Epost: Info@epmembran.se

Hemsida: www.Epmembran.se